



Oleoterra

| naturbelassene Leder

| *natural leather*

Oleoterra

eder, Stärke 1,2 bis 1,5 mm / buffed natural leather protected with oil and waxes, strength 1,2 to 1,5 mm

Technische Werte/ technical specifications	Meßmethode/ test methods	Werte/ values
Dieke/thickness	DIN EN ISO 2589	1,2 mm - 1,5 mm
Flächengewicht/mass per unit area	DIN EN ISO 2420	1.000 ± 200 g/m ²
Reibechtheit/rub fastness trocken/dry nass/wet pH = 8	EN ISO 11640 50 cycles 20 cycles 20 cycles	≥ 4 grey scale ≥ 4 grey scale ≥ 4 grey scale
Zugfestigkeit/tensile strength Höchstzugkraft/maximum tensile force Bruchdehnung/breaking elongation	EN ISO 3376-2	≥ 80 N 30 - 70%
Dauerknickverhalten/flexion 30.000 Knickungen/flexes	EN ISO 5402	Keine Beschädigung/ no damage
Weiterreißkraft/tear strength	EN ISO 3377-2	≥ 25 N
Haftung der Zurichtung/adhesion of finish	EN ISO 11644	≥ 4 N/cm
Stichausreißkraft/stitch tear strength	EN ISO 23910	≥ 50 N
Lichtecktheit/light fastness	EN ISO 105-B06	≥ 5 blue scale
Geruchsprüfung/smelling test	VDA 270-C3	≤ 3 grade
Brennprüfung/flammability	DIN EN ISO 1021 1+2 BS 5852 source 3 California TB 117 IMO A.652 Annex 1 Part 8	OK
Hautgröße circa/average size		5 qm/sqm
Lieferung ab circa/minimum delivery		5 qm/sqm



2985 silk



2992 ginger



2986 indian red



2983 sandstone



2990 moccasin



2982 olive



2991 reddish brown



2989 coffee



2980 granite



2998 mink



Kollektionsmuster sind keine Urmuster. Kleine Farbabweichungen sind möglich.
Swatches are no master samples. Small differences may occur.