




Möbelleder *Upholstery Leather*



Softerra

| naturbelassene Leder

| *natural leather*

Softerra

rein anilin, vollnarbig, Stärke 1,4 bis 1,6 mm / *pure aniline, full grain, strength 1,4 to 1,6 mm*

Technische Werte/ technical specifications	Meßmethode/ test methods	Werte/ values
Dicke/ <i>thickness</i>		1,4 mm - 1,6 mm
Reibechtheit/ <i>rub fastness</i> trocken/ <i>dry</i> nass/ <i>wet</i> pH = 8	DIN EN ISO 11640 50 cycles 20 cycles 20 cycles	≥ 3 grey scale ≥ 3 grey scale ≥ 3 grey scale
Weiterreißkraft/ <i>tear strength</i>	DIN 53329	≥ 20 N/mm
Lichtechtheit/ <i>light fastness</i>	DIN EN ISO 105-B02	≥ 3
Brennprüfung/ <i>flammability</i>	DtN EN 1021 1+2	OK
Hautgröße <i>circa/average size</i>		5 qm/sqm
Lieferung ab <i>circa/minimum delivery</i>		5 qm/sqm



2911 Softerra natur



2914 Softerra tabak



2915 Softerra cognac



2916 Softerra dunkelbraun



2912 Softerra braun



2913 Softerra schwarz



Kollektionsmuster sind keine Urmuster. Kleine Farbabweichungen sind möglich.
Swatches are no master samples. Small differences may occur.